




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : F28F 21/06	A1	(11) International Publication Number: WO 98/11398 (43) International Publication Date: 19 March 1998 (19.03.98)
(21) International Application Number: PCT/CA97/00641 (22) International Filing Date: 9 September 1997 (09.09.97) (30) Priority Data: 60/026,110 11 September 1996 (11.09.96) US 08/922,913 3 September 1997 (03.09.97) US (71) Applicant: DUPONT CANADA INC. [CA/CA]; 7070 Mississauga Road, Mississauga, Ontario L5M 2H3 (CA). (72) Inventor: DOSHI, Shailesh; 1060 Redwood Crescent, Kingston, Ontario K7P 1Y9 (CA). (74) Agent: VAN ZANT, Joan, M.; Van Zant & Associates, Suite 1407, 77 Bloor Street West, Toronto, Ontario M5S 1M2 (CA).	(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.	

(54) Title: DIMENSIONALLY STABLE TUBE-TYPE PLASTIC HEAT EXCHANGERS



(57) Abstract

Plastic tube-type heat exchanger structures are made with partially crystallized partially aromatic polyamides of high glass transition temperature. The structures are then annealed to further crystallize the polyamides, causing shrinkage and building up residual tensile stresses. These stresses counteract the swelling caused by water absorption and temperature rise during use of the heat exchanger and keep the structures dimensionally stable.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DIMENSIONALLY STABLE TUBE-TYPE PLASTIC HEAT EXCHANGERS

BACKGROUND OF THE INVENTION

5 This invention relates to heat exchangers, specifically tube-type heat exchangers made using tubes made from thermoplastic compositions, a major portion of which comprises certain types of partially aromatic polyamides or copolyamides, and a process to manufacture these heat exchangers.

 Heat exchangers fabricated from metals are well known, and are used in a
10 wide variety of automotive and other transportation vehicles, chemical processing, air conditioning, and refrigeration end-uses where there is a need to exchange heat between two fluid streams without bringing them into direct contact with each other. Metals have the advantage that they provide rapid conduction of heat through the wall, and generally possess high stiffness and strength properties.
15 However, they are subject to corrosion from chemical attack. Engineering thermoplastics, especially polyamides, possess good chemical resistance and stiffness and strength properties at elevated temperatures. It is thus desirable to construct heat exchangers out of these thermoplastic materials.

 Heat exchangers formed from thermoplastics, and methods for their
20 manufacture are known. For example, US patents 4,955,435; 5,469,915 and 5,499,676 disclose a number of panel heat exchangers formed from thermoplastics, preferable polyamides. US patents 4,923,004 and 5,078,946 disclose a compact heat exchanger made from a thermoplastic, preferably a polyamide, and a method to manufacture it.

25

Tube-Type Thermoplastic Heat Exchangers

 The present invention relates to a tube-type exchanger formed from thermoplastics. These heat exchangers consist of structures where a multitude of tubes running lengthwise are arranged in a spaced apart manner and are integrally
30 bonded to two manifolds at their ends. The manifolds are provided with a fluid inlet through which a first fluid enters and flows through the tubes, and a fluid outlet through which this first fluid exits. A second fluid flows around the tubes on their outside such that heat exchange is facilitated between the first and the second fluids across the wall of the tubes. Direct contact between the fluids is
35 prevented by the tube walls and construction of the manifolds.

 In cases where the second fluid requires containment, a thermoplastic shell may be provided that extends between the two manifolds enveloping the tubes and is in flow communication with the inlets and outlets for the second fluid. If the

second fluid does not require containment, as in the case of ambient air, it is not necessary to provide a shell.

DESCRIPTION OF THE PROBLEM

5 Tube-type heat exchangers with tubes constructed out of polyamides suffer from one drawback. Upon absorption or desorption of moisture or other polar chemicals such as alcohols, the tubes exhibit dimensional changes. Depending on the design and exposure conditions, these dimensional changes are often non-uniform, i.e., some tubes exhibit larger dimensional changes than others.

10 Dimensional changes can also occur due to thermal expansion/contraction, and depending on temperature gradients, these changes can be non-uniform as well. In a heat exchanger structure with constrained span between the manifolds, the longer tubes develop bends and curves to accommodate the different length. This phenomenon has the following negative consequences:

- 15 (a) It leads to poor appearance of the heat exchanger
 (b) It creates gaps between the tubes through which the external fluid can bypass, and thus significantly reduce the overall heat transfer performance.

BRIEF DESCRIPTION OF THE DRAWINGS

20 A tube-type heat exchanger without a shell is illustrated in Fig. 1, the sole figure of the drawing, where element 1 are the tubes arranged lengthwise between manifolds 2 and 3. Element 4 is a frame which provides structural support to the unit, and maintains the span of the tubes between the two manifolds.

SUMMARY OF THE INVENTION

25 The present invention provides a tube for use in a heat exchanger, said tube being made from a thermoplastic composition, which composition comprises at least 50% by weight partially aromatic melt processable polyamides or copolyamides made from aliphatic and aromatic monomers with, on a molar basis,
30 25% to 65% of the monomers being aromatic and wherein, polyamide or copolyamide has a glass transition temperature of 65°C or higher.

 The invention also provides heat exchanger made from such tube and a process for manufacturing a tube-type plastic heat exchanger in which curving and bending of the tubes that can occur in service environments due to pickup or loss
35 of moisture or polar chemicals and thermal expansion is prevented.

DETAILED DESCRIPTION

A solution has been found to the above problem by making heat exchanger tubes out of certain types of partially aromatic melt processable polyamides or copolyamides that have relatively high glass transition temperature. When these
5 polymers are melt formed into tubing, and quenched, they attain only a fraction of the total crystallinity that they are capable of attaining. Also, they possess a relatively high level of residual stress resulting from the forming process. Annealing of these tubes at a temperature above their glass transition temperature causes relaxation of the residual stress and further crystallization of the material.
10 These process lead to shrinkage in tubing dimensions.

In various aspects, the invention involves:

- 15 (a) constructing a tube-type heat exchanger using tubing made from thermoplastic compositions, a major portion of which comprises the above-described polyamides/copolyamides. The tubing has only a fraction of the total crystallinity that the polyamide is capable of attaining, and can have a significant level of residual stress resulting from the tube forming process. The heat exchanger is constructed with a rigid frame such that the span of the tubes between the two
20 manifolds is fixed to a predetermined length.
- (b) subjecting the heat exchanger to an annealing treatment by exposing it to an appropriate temperature above the glass transition temperature of the polyamide. The annealing temperature can be substantially above the glass transition temperature in order for annealing to be
25 completed in a shorter duration of time.

Annealing causes the polyamide/copolyamide to crystallize further and relieve the residual stress present in the tubing from the forming process. As a result of these processes, the tubing undergoes contraction. However, since the
30 span of the tubes between the two manifolds is fixed to the predetermined length, the contraction introduces tension in the assembly. The amount of contraction is dependent upon the specific type of polyamide used and the degree of crystallinity and residual stress in the tubing prior to the annealing step. It is important to choose the polymers and design the assembly such that the amount of contraction
35 upon annealing is larger than the maximum amount of expansion that is expected to occur in the service environment, yet not so high that the resulting tension could cause failure of the tubes or tube-to-manifold bonds. In the present invention, it is desirable that the amount of contraction upon annealing is in the

range of 1 to 5 times the magnitude of the maximum amount of potential expansion that can occur when dry tubes become saturated with water. Also, annealing should be done in such a way that all the tubes are heated uniformly, and thus are able to contract at a uniform rate. If this is not achieved, some tubes
5 may anneal and contract faster than others, and could cause buckling of the longer tubes.

When such a heat exchanger is put into service, the tubes would undergo expansion due to absorption of moisture or other polar chemicals and/or temperature rise encountered in the service environment. However, this
10 expansion simply leads to relaxation of some of the tension built up by the annealing process as opposed to causing bends and curves in the tubes. The exchanger is thus able to retain its appearance and heat transfer performance in the service environment.

15 **Partially Aromatic Melt Processable Polyamides and Copolyamides**

Partially aromatic melt processable polyamides or copolyamides used in the present invention are polymers formed from aliphatic and aromatic monomers such as diamines, dicarboxylic acids or their derivatives, aminocarboxylic acids and lactams such that, on a molar basis, at least 25% of the monomers are
20 aromatic in nature.

Examples of aliphatic diamines are hexamethylene diamine, 2-methyl pentamethylene diamine, 1-4 diaminobutane, 2-2-4 trimethylhexamethylene diamine, 2-2-4 trimethylpentamethylene diamine, 5-amino-1-3-3-trimethylcyclohexane methylamine, bis-aminomethyl cyclohexane etc. Examples
25 of aromatic diamines are m-xylene diamine, p-xylene diamine, m-phenylene diamine, and p-phenylene diamine.

Examples of aliphatic dicarboxylic acids are adipic acid, sebacic acid, dodecanedioic acid, etc. Examples of aromatic dicarboxylic acids and their derivatives are terphthalic acid, isophthalic acid, dimethyl terphthalate, and 2-6
30 naphthalene dicarboxylic acid.

Examples of aliphatic aminocarboxylic acids include 11-aminodecanoic acid, and 4-aminocyclohexyl acetic acid. Examples of aromatic aminocarboxylic acids include p-aminomethyl benzoic acid, 4-aminophenyl acetic acid.

Examples of aliphatic lactams are caprolactam, laurolactam, and bicyclic endoethylene caprolactam. An example of aromatic lactam is oxinadole.
35

These polyamides and copolyamides have high glass transition temperature such as about 65°C or higher. There are several ways of analytically determining the glass transition temperature of polymers. One method uses

dynamic mechanical analysis (DMA) of polymer samples. In the following data, the temperature at which the storage modulus in dynamic mechanical analysis (DMA) exhibits a change in slope is used to indicate the glass transition temperature.

5 It is desirable that the molar aromatic content of the monomers used in forming a polyamide or a copolyamide be below 65%. At higher aromatic content, the melting point of the polymer is too high to be melt processable. Also, such a polymer is likely to have low overall degree of crystallinity, and thus, will not exhibit adequate contraction upon annealing.

10 Table I lists several such partially aromatic polyamides and copolyamides along with their constituent monomers, their molar aromatic content, and approximate glass transition temperatures. Some aliphatic polyamides are also listed for comparison.

Table I

Partially Aromatic Polyamides/Copolyamides

Polyamide/ Copolyamide	Monomer (molar ratio)	Glass Trans. Temp. (°C)	Molar Aromatic Content (%)
6T/DT (50/50)	HMD(50):2-MPMD(50):TPA(100)	125	50
6T/DT (55/45)	HMD(55):2-MPMD(45):TPA(100)	127	50
6T/DT (30/70)	HMD(30):2-MPMD(70):TPA(100)	135	50
6T/66 (55/45)	HMD(100):TPA(55):AA(45)	80	27.5
6T/66 (65/35)	HMD(100):TPA(65):AA(35)	76	32.5
10T	DMD(100):TPA(100)	100	50
12T	DDMD(100):TPA(100)	85	50
6T/6 (70/30)	HMD(70):TPA(70):CAPRO(30)	85	41.2
6T/DT/612 (55/10/35)	HMD(90):2-MPMD(10):TPA(65): DDDA(35)	65	32.5
6T/DT/612 (50/25/25)	HMD(75):2-MPMD(25):TPA(75): DDDA(25)	75	37.5
6T/DT/610 (55/10/35)	HMD(90):2-MPMD(10):TPA(65): DDDA(35)	66	32.5
6T/DT/610 (50/30/20)	HMD(70):2-MPMD(30):TPA(80): AA(20)	103	40
6T/6I/66 (65/25/10)	HMD(100):TPA(65):IPA(25): AA(10)	105	45
MXD6	MXD(100):AA(100)	102	50
TMDT	TMD(100):TPA(100)	148	50

Aliphatic Polyamides

Polyamide/ Copolyamide	Monomer (molar ratio)	Glass Trans. Temp. (°C)	Molar Aromatic Content (%)
66	HMD(100):AA(100)	48	0
612	HMD(100):DDDA(100)	45	0
6	Epsilon Capro (100)	41	0

In the previous Table, the following abbreviations have been used:

	HMD	Hexamethylene diamine
	2-MPMD	2-Methyl pentamethylene diamine
5	TPA	Terephthalic acid
	AA	Adipic Acid
	DMD	Decamethylene diamine
	DDMD	Dodecamethylene diamine
	Capro	Caprolactam
10	DDDA	Dodecanedioic acid
	DDA	Decanedioic acid
	IPA	Isophthalic acid
	MXD	Metaxylene diamine
	TMD	Trimethy hexamethylene diamine
15	6T	polymer molecular unit formed from HMD and TPA
	DT	polymer molecular unit formed from 2-MPMD and TPA
	66	polymer molecular unit formed from HMD and AA
	10T	polymer molecular unit formed from DMD and TPA
	12T	polymer molecular unit formed from DDMD and TPA
20	6	polymer molecular unit formed from Capro
	612	polymer molecular unit formed from HMD and DDDA
	610	polymer molecular unit formed from HMD and DDA

It should be noted that the above polyamides/copolyamides may be used by themselves or in compositions with other polymers where they form the major portion of the polymeric formulation. Also, they may be modified by the incorporation of toughening agents, melt viscosity enhancers, reinforcements, filters, and other additives to enhance their melt viscosity, processability, thermal/oxidative/chemical stability, physical properties and mechanical properties. For example, additives with reactive functional groups such as epoxy, acid or anhydride are often used to enhance melt viscosity of polyamides. Elastomeric materials with such functional groups are often used to enhance toughness properties of polyamides. Glass fibers, particulate minerals, etc. may be used to enhance stiffness and strength properties of polyamides. A common way of preparing these compositions involves melting and mixing the ingredients in appropriate proportions in an extruder, preferable a twin screw extruder.

Tubes Formed from Partially Aromatic Melt Processable Polyamides or Copolyamides:

5 Polymeric formulations based on the above-described partially aromatic
melt processable polyamides or copolyamides may be formed into tubing by
known techniques. A typical process involves plasticating the material into melt
in an extruder, and extruding the melt through a die that has an annular opening of
appropriate dimensions. The melt tube exiting from the die enters a water
quenching bath where it solidifies. In case of small diameter tubing, dimensions
10 of the tubing can be controlled by blowing air through the die into the tubing, and
an open water tank can be used for quenching. Alternatively, vacuum sizing is
used where vacuum is applied in the quench tank with or without blowing air into
the tubing. In the latter case, a sizer designed in the form of a short metal tube
with an internal diameter corresponding to the desired outer diameter of the plastic
15 tubing is used at the inlet to the quench tank to solidify the melt tubing to the
desired dimensions.

Because of the high glass transition temperature, the tubing made out of
the above-described thermoplastic polyamides or copolyamides develops only a
fraction of the crystallinity that the polyamide is capable of attaining. The tubing
20 is also likely to have a significant level of residual stress resulting from the tube
forming process. An annealing step is required for the tubing to develop its
complete crystallinity, and relieve the residual stress. The tubing undergoes
contraction upon annealing. The amount of contraction is dependent upon the
specific type of polyamide used, degree of crystallinity and residual stress in the
25 tubing prior to the annealing step. To be useful in the present invention, it is
important to choose the polymer formulations and form them into tubing such that
the amount of contraction upon annealing is larger than the maximum amount of
expansion that is expected to occur in the service environment, yet not so high that
the resulting tension could cause failure of the tubes or tube-to-manifold bonds in
30 a fabricated heat exchanger. Specifically, it is desirable that the amount of
contraction upon annealing is in the range 1 to 5 times the magnitude of the
maximum amount of expansion that can potentially occur when dry tubes become
saturated with water.

35 **Dimensionally Stable Tube-Type Plastic Heat Exchanger:**

A tube-type plastic heat exchanger is constructed by arranging a multitude
of tubes lengthwise in a spaced apart manner between two manifolds, and

integrally connecting them to the manifolds. The tubes can be connected to the manifolds using suitable bonding techniques such as adhesive bonding or welding.

The invention involves:

- 5 (a) constructing a tube-type heat exchanger using tubing made from thermoplastic formulations based on the above described polyamides/copolyamides. The tubing has only a fraction of the total crystallinity that the polyamide is capable of attaining, and may have a significant level of residual stress resulting from the tube forming process. The heat exchanger is constructed with a rigid frame such
10 that the span of the tubes between the two manifolds is fixed to a predetermined length.
- 15 (b) subjecting the heat exchanger to an annealing treatment by exposing it to an appropriate temperature above the glass transition temperature of the polyamide. The annealing temperature can be substantially above the glass transition temperature in order for annealing to be completed in a shorter duration of time.

20 Annealing causes the polyamide/copolyamide to crystallize further and relieve the residual stress present in the tubing from the forming process. As a result of these process, the tubing undergoes contraction. However, since the span of the tubes between the two manifolds is fixed at a predetermined length, the contraction introduces tension in the assembly. The amount of contraction is dependent upon the specific type of polyamide used, degree of crystallinity and
25 residual stress in the tubing prior to the annealing step. It is important to choose the polymers and design the assembly such that the amount of contraction upon annealing is larger than the maximum amount of expansion that is expected to occur in the service environment, yet not so high that the resulting tension could cause failure of the tubes or tube-to-manifold bonds. Also, annealing should be
30 done in such a way that all of the tubes are heated uniformly, and thus are able to contract at a uniform rate. If this is not achieved, some tubes may anneal and contract faster than others, and could cause buckling of the longer tubes.

When such a heat exchanger is put into service, the tubes would undergo expansion due to absorption of moisture or other polar chemicals and/or
35 temperature rise encountered in the service environment. However, this expansion simply leads to relaxation of some of the tension built up by the annealing process as opposed to causing bends and curves in the tubes. The

exchanger is thus able to retain its shape and appearance, and its heat transfer performance in the service environment.

Parts, proportions and percentages herein are by weight except where indicated otherwise.

5

Example 1:

Materials based on a high molecular weight aliphatic polyamide, namely 66, and a partially aromatic copolyamide, namely 6T/DT (50/50) were used to make heat exchanger tubing with an outside diameter of about 3.65 mm and wall thickness of 0.19-0.22 mm.

66 has a low glass transition temperature of about 48°C. Tubing made out of this material was expected to attain essentially its full crystallinity during the extrusion quenching step. Also, the residual stress level in the tubing was expected to be relatively low. The copolyamide 6T/DT (50/50) was toughened with approximately 15% functionalized and 5% non-functionalized ethylene-propylenehexadiene elastomers. The functionalized toughener was grafted with about 1.75% maleic anhydride by weight. This copolyamide has a relatively high glass transition temperature of about 125°C. As a result, during the extrusion quenching step, the tubing made out of this material is capable of achieving. It was also expected to have a high level of residual stress.

The additional degree of crystallinity that a material is capable of attaining upon annealing, and the level of residual stress in the tubing can be assessed by measuring the amount of contraction associated with the annealing treatment. For this purpose, representative tubing samples of the above materials were subjected to an annealing treatment by exposing them to a temperature of 180°C for five minutes in Nitrogen environment, and change in their lengths were measured after cooling to room temperature. Also, dimensional change in the annealed samples upon pickup/loss of water was characterized by subjecting them to repeated moisture conditioning and drying treatments, and calculating an average change in length associated with going from a dry to a near-saturated state. These results are summarized in Table 2.

Table 2

Material	Composition	Contraction Upon Annealing (mm/m of tubing)	Expansion Upon Moisture Absorption of Annealed Tubes going from dry to near-saturated state (mm/m of tubing)
I	66	6.4	22.0
II	Toughened 6T/DT (50/50)	45.4	16.8

5 The results confirm the expectation that upon extrusion quenching, 66 tubing attained substantially all of its crystallinity, and had a relatively low level of residual stress, while toughened 6T/DT (50/50) tubing only achieved a fraction of its attainable crystallinity and had a high level of residual stress.

10 It is worth noting that contraction due to annealing of tubes made out of toughened 6T/DT polymer is about 2.7 times the maximum amount of expansion that is likely to occur due to moisture saturation.

15 The dimensional change due to thermal expansion resulting from a rise in temperature of 23°C to 100°C for the tubing of both materials is estimated to be of the order of 8.3 mm/m. Thus, for a service environment involving a temperature of 100°C and humidity-saturated state, the contraction due to annealing for the toughened 6T/DT (50/50) tubing is about 1.8 times the magnitude of the total expansion that could potentially occur due to both moisture pickup and temperature rise.

20 A tube-type heat exchanger approximately 0.74 m wide by 0.33 m high by 0.09 m thick was constructed from 66 tubing by arranging 329 tubing pieces horizontally between two manifolds capturing a span of 0.71 m. This exchanger was not annealed since the above data showed that its tubing had substantially achieved all of its potential crystallinity and the level of residual stress in the tubing was relatively low. The frame of the exchanger was provided with
25 tensioning springs so as to maintain tension against potential expansion in the tubes. It was tested in a service type environment by circulating about 65°C hot water inside the tubes and air around them. In spite of the tensioning springs in the frame, within a few hours, some of its tubes developed bends and curves due to non-uniform growth.

A similar exchanger was constructed from toughened 6T/DT (50/50) tubing. Its frame was designed such that one manifold could move inwards by 6.4 mm in response to 0.704m. No tensioning springs were provided in this heat exchanger. Upon fabrication, the whole exchanger was annealed at 185°C for 10 minutes in an oven. Upon annealing, the moveable tubesheet pulled in through the allowed distance, and all of the tubes felt quite tight. None of the tubes showed any sign of buckling, indicating that the annealing had occurred in a uniform manner. The exchanger was tested in a service type environment as described above. Hot water at about 65°C was circulated during the day time allowing the tubes to absorb moisture, while circulation was stopped during the night time allowing the tubes to dry out. The test lasted for more than 21 days. Throughout the test, the tubes stayed straight, and did not develop any curves or bends.

15 **Example 2:**

Three polymeric formulations were prepared using a partially aromatic copolyamide 6T/DT (30/70) as follows.

	<u>Material</u>	<u>Composition (by weight%)</u>
20	III	95% 6T/DT (30/70) + 5% styrene maleic anhydride copolymer
	IV	80% 6T/DT (30/70) + 15% ethylene-propylene-hexadiene elastomer functionalized with 1.75% maleic anhydride + 5% ethylene-propylene-hexadiene elastomer
25	V	85% 6T/DT (30/70) + 5% styrene-maleic anhydride copolymer + 6.7% ethylene-propylene-hexadiene elastomer functionalized 1.75% maleic anhydride + 3.3% ethylene-propylene-hexadiene elastomer

Tubes with an outside diameter of about 3.65 mm and wall thickness of about 0.19 - 0.22 mm were made from above materials by extrusion and quenching. Representative tubing samples were subjected to an annealing treatment at 205°C for 5 minutes in a nitrogen atmosphere, and the amount of contraction was measured as described in Example 1. Also, the dimensional change due to absorption from almost dry to near saturated state was characterized as described in Example 1. The results of these measurements are presented in Table 3.

Table 3

Material	Contraction upon Annealing (mm/m of tubing)	Expansion upon moisture absorption of annealed tubes going from almost dry to near saturated state (mm/m of tubing)
III	190	21.2
IV	262	21.6
V	272	18.6

5 The results show that the amount of contraction upon annealing in these tubes is about 9 to 14 times the maximum amount of expansion that could occur due to moisture pickup. This amount of contraction is quite large, and would require appropriately designed structures or geometrics in a heat exchanger to ensure that the contraction due to annealing occurs in a uniform manner, and does not lead to excessive tensioning of the assembly. This can be accomplished, for instance, by designing the manifold and heat exchanger frame assembly such that one of the manifolds is moveable through a predetermined distance before tensioning of the assembly begins.

15 Example 3

Several polymeric formulations were prepared using a partially aromatic copolyamide, 6T/DT (50/50), an aliphatic polyamide, N66, styrene-maleic anhydride copolymer (SMA) and tougheners based on ethylene-propylene-hexadiene elastomer either functionalized with 1.75% maleic anhydride (MA-g-EPDM) or in non-functionalized (EPDM) form. The partially aromatic copolyamide 6T/DT (50/50) formed the major portion of each formulation.

	Material	Composition
25	VI	70% 6T/DT (50/50) + 10% N66 + 15% MA-g-EPDM
	VII	75% 6T/DT (50/50) + 10% N66 + 5% SMA + 6.7% MA-g-EPDM + 3.3% EPDM
	VIII	65% 6T/DT (50/50) + 10% N66 + 5% SMA + 15% MA-g-EPDM + 5% EPDM
30	IX	60% 6T/DT (50/50) + 20% N66 + 15% MA-g-EPDM + EPDM

- X 65% 6T/DT (50/50) + 20% N66 + 5% SMA + 6.7% MA-g-EPDM + 3.3% EPDM
- XI 65% 6T/DT (50/50) + 20% N66 + 2.5% SMA + 8.5% MA-g-EPDM + 4% EPDM
- 5 XII 50% 6T/DT (50/50) + 30% N66 + 15% MA-g-EPDM + 5% EPDM
- XIII 60% 6T/DT (50/50) + 30% N66 + 5% SMA + 5% MA-g-EPDM
- XIV 55% 6T/DT (50/50) + 30% N66 + 5% SMA + 6.7% MA-g-EPDM + 5% EPDM
- 10 XV 45% 6T/DT (50/50) + 30% N66 + 5% SMA + 15% MA-g-EPDM + 5% EPDM

20 Tubings with an outside diameter of about 3.65 mm and wall thickness of about 0.19 - 0.22 mm were made from the above material by extrusion and quenching. Representative samples of these tubings were subjected to an annealing treatment at 190°C for about 10 minutes in a Nitrogen environment, and the amount of contraction was measured as described in Example 1. Also, the dimensional changes due to moisture absorption from almost dry to near saturated state was characterized for each material as described in Example 1. The results are presented in Table 4.

Table 4

Material	Contraction upon Annealing (mm/m of tubing)	Expansion upon moisture absorption of annealed tubes going from almost dry to near saturated state (mm/m of tubing)
VI	28.5	15.5
VII	19.8	14.2
VIII	31.3	13.8
IX	55.3	18.3
X	59.0	15.8
XI	38.0	17.3
XII	25.2	21.4
XIII	54.7	17.3
XIV	37.5	18.9
XV	39.2	18.3

The results show that all of the above materials exhibit contraction upon annealing in the range of 1.2 to 3.7 times the maximum amount of expansion that is likely to occur due to moisture saturation. In a properly designed tube-type heat exchanger, these materials would thus enable one to impart tension in the tubes by the annealing technique described here, and thus retain appearance and heat transfer performance of the heat exchanger.

The thermal expansion due to an increase in temperature from 23°C to 100°C for these tubes is estimated to be of the order of 83.3 mm/m. In case of materials VII and XII, the amount of contraction due to annealing is larger than the maximum amount of expansion that could occur due to moisture pickup. In applications where large thermal expansion is not expected, these materials would be adequate to use. In applications where thermal expansion of the above magnitude is expected to accompany the expansion due to moisture saturation, the tension built up by the above annealing technique may not be adequate to retain the appearance of the tubes against the total expansion.

Example 4:

Polymeric formulations were prepared by compounding 5% and 10% by weight of a liquid crystalline copolymer (LCP) viz. Poly (4,4'-buphenldiol/ hydroquinone/ 4-hydroxybenzoic acid/ terephthalic acid/ 2,6-naphthalene dicarboxylic acid/ 6-hydroxy-2-naphthalene carboxylic acid/ acetic anhydride) as reinforcing agent into the toughened partially aromatic copolyamide of Example 1 (material II). Tubes with an outside diameter of about 3.65 mm and wall thickness of 0.19 - 0.22 mm were made from these materials by extrusion and quenching. During the extrusion process, LCP is expected to form reinforcing fibrils inside the copolyamide matrix. Representative samples were subjected to an annealing treatment at 190°C for about 10 minutes in a Nitrogen environment, and the amount of contraction was measured as described in Example 1. Also, the dimensional changes due to moisture absorption form almost dry to near saturated state was characterized for each material as described in Example 1. The results are presented in Table 5.

Table 5

Material Moisture Annealed	Composition (by weight)	Contraction upon Annealing (mm/m of tubing)	Expansion upon moisture absorption of annealed tubes going from almost dry to near saturated state (mm/m of tubing)
XVI	Toughened 6T/DT (50/50) + 5% LCP	34.1	13.1
XVII	Toughened 6T/DT (50/50) + 10% LCP	24.3	11.1

It is interesting to note that the contraction of these tubes due to annealing is somewhat smaller than that for the tubing made out of toughened 6T/DT (Material II) that did not have any LCP. This may be because presence of LCP promotes crystallization of the copolymer prior to quenching so that the amount of additional crystallization resulting upon annealing is lower. Also, the expansion of these tubes due to moisture absorption is smaller than that for the tubing made out of toughened 6T/DT (Material II). This is likely to be due to reinforcing effect of the LCP fibrils.

The results show that the above materials exhibit contraction due to annealing that is 2.2 to 2.6 times the expansion due to moisture pickup. Also, because of the reinforcing effects of LCP fibrils, thermal expansion in these material due to a rise in temperature of 23°C to 100°C is expected to be smaller than 8.3 mm/m estimated to be for materials that do not have LCP reinforcement. In a properly designed tube-type heat exchanger, these materials can be used in conjunction with the annealing technique described here to impart tension in the tubing, and hence, maintain the appearance and heat transfer performance of the heat exchanger.

CLAIMS:

1. A tube for use in a heat exchanger, said tube made from a thermoplastic composition, which composition comprises at least 50% by weight partially aromatic melt processable polyamides or copolyamides made from aliphatic and aromatic monomers with, on a molar basis, 25% to 65% of the monomers being aromatic, and wherein said polyamide or copolyamide has a glass transition temperature of 65°C or higher.
2. The tube of Claim 1 which has the property that when an as-formed, unannealed tube is subjected to an annealing treatment at a temperature equal to above the glass transition temperature of the polyamide or copolyamide, it exhibits shrinkage that is about 1 to 5 times as great as the maximum amount of potential expansion that would occur in dry tubes when they become saturated by water.
3. A tube-type plastic heat exchanger comprising tubes of Claim 1.
4. The tube-type plastic heat exchanger comprising tubes of Claim 2.
5. A process for manufacturing a tube-type plastic heat exchanger in which curving and bending of the tubes that can occur in service environments due to pickup or loss of moisture or polar chemicals and thermal expansion is prevented by:
 - (a) providing tubes made from a thermoplastic composition, which composition comprises at least 50% by weight partially aromatic melt processable polyamides or copolyamides made from aliphatic and aromatic monomers with, on a molar basis, 25% to 65% of the monomers being aromatic, and wherein said polyamide or copolyamide has a glass transition temperature of 65% or higher, such tubes having the property that when as-formed, unannealed tubes are subjected to an annealing treatment at a temperature above the glass transition temperature of the polyamide or copolyamide, they exhibit shrinkage that is about 1 to 5 times in magnitude compared to the maximum amount of potential expansion that would occur in dry tubes when they become saturates with water;

(b) arranging the as-formed, unannealed tubes lengthwise in a spaced apart manner between two manifolds, and integrally connecting the ends of the tubes to the two respective manifolds;


5

(c) said heat exchanger having a rigid frame such that the span of the tubes between the two manifolds is fixed at a predetermined length; and

(d) subjecting the heat exchanger to an annealing treatment at a temperature above the glass transition temperature of the polyamide or copolyamide so as to create pre-stressing in the tubes due to contraction against the rigid frame.

10

FIG. 1



INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 97/00641

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 F28F21/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 F28F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 291 322 A (DUPONT CANADA INC.) 17 November 1988 cited in the application see page 4, line 20 - page 4, line 43 see page 5, line 65 - page 6, line 21; figures 1-5 & US 4 923 004 A (DUPONT CANADA INC) 8 May 1990	1-5
A	EP 0 469 435 A (EMS-INVENTA AG) 5 February 1992 see page 2, line 50 - page 4, line 49	1-5
A	WO 94 20564 A (DUPONT CANADA INC.) 15 September 1994 see page 3, line 31 - page 10, line 30 -/-	1-5

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 December 1997

Date of mailing of the international search report

16/12/1997

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Beltzung, F

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 97/00641

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 277 376 A (AKZO NV) 10 August 1988 see page 3, line 14 - page 3, line 38 ----	1-5
A	WO 89 10948 A (RAYCHEM LTD) 16 November 1989 see page 7, line 16 - page 14, line 4 -----	1-5

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 97/00641

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 291322 A	17-11-88	AU 599485 B	19-07-90
		AU 1610288 A	17-11-88
		CA 1316527 A	20-04-93
		DE 3866155 A	19-12-91
		JP 63311084 A	19-12-88
		KR 9607986 B	17-06-96
		US 4923004 A	08-05-90
		US 5078946 A	07-01-92
EP 469435 A	05-02-92	DE 4023968 A	30-01-92
		DE 59104377 D	09-03-95
		JP 4253727 A	09-09-92
		KR 9411164 B	24-11-94
		US 5177177 A	05-01-93
WO 9420564 A	15-09-94	US 5502155 A	26-03-96
		AU 6152894 A	26-09-94
EP 277376 A	10-08-88	JP 63154651 A	27-06-88
		US 4851562 A	25-07-89
		US 4980444 A	25-12-90
WO 8910948 A	16-11-89	AT 146507 T	15-01-97
		CA 1335009 A	28-03-95
		DE 68927572 D	30-01-97
		DE 68927572 T	24-07-97
		EP 0414748 A	06-03-91
		JP 3504135 T	12-09-91
		US 5296558 A	22-03-94